

# **NROM FLASH MEMORY DEVICES ON ULTRATHIN SILICON**

## **TECHNICAL FIELD OF THE INVENTION**

**[0001]** The present invention relates generally to memory devices and in particular the present invention relates to nitride read only memory flash memory devices.

## **BACKGROUND OF THE INVENTION**

**[0002]** The increased speed and capability of computers and other electronic devices requires better performance from the integrated circuits that make up a device. One way to make the integrated circuits faster is to reduce the size of the transistors that make up the device. However, as transistors are made smaller and faster, delays through the connections between the transistors becomes greater in relation to the speed of the transistor.

**[0003]** An alternative technique to speed up integrated circuits is to use alternative semiconductors. For example, silicon-on-insulator (SOI) technology provides a 25 – 35% performance increase over equivalent CMOS technologies. SOI refers to placing a thin layer of silicon on top of an insulator such as silicon oxide or glass. The transistors would then be built on this thin layer of SOI. The SOI layer reduces the capacitance of the transistors so that they operate faster.

**[0004]** Figure 1 illustrates a typical prior art SOI semiconductor. The transistor is formed in the silicon layer 101 that is over the insulator 102. The insulator is formed on top of the substrate 103. Within the silicon layer 101, the drain/source regions 105 and 106 are formed. The gate 107 is formed above the partially depleted channel 109. A floating body 110 is within the depleted region 112 and results from the partial depletion.

**[0005]** SOI technology, however, imposes significant technical challenges. The silicon film used for SOI transistors must be perfect crystalline silicon. The insulator layer, however, is not crystalline. It is very difficult to make perfect crystalline silicon-on-oxide or silicon with other insulators since the insulator layer's crystalline properties are so

different from the pure silicon. If perfect crystalline silicon is not obtained, defects will find their way onto the SOI film. This degrades the transistor performance.

[0006] Additionally, floating body effects in partially depleted CMOS devices using SOI technology are undesirable in many logic and memory applications. The floating bodies cause threshold voltages and switching speeds to be variable and complex functions of the switching history of a particular logic gate. In dynamic logic and DRAM memories, the floating bodies cause excess charge leakage and short retention times that can cause data loss. In conventional flash memories and NROM devices, the floating bodies cause reduced erase fields and slower erase times.

[0007] For the reasons stated above, and for other reasons stated below which will become apparent to those skilled in the art upon reading and understanding the present specification, there is a need in the art for a way to eliminate floating body effects in CMOS devices incorporating SOI technology.

## SUMMARY

[0008] The above-mentioned problems with eliminating floating body effects and other problems are addressed by the present invention and will be understood by reading and studying the following specification.

[0009] The present invention encompasses an NROM transistor having an ultra-thin silicon-on-insulator substrate. The silicon has two doped source/drain regions separated by a normally fully depleted body region. The doped regions are a different conductivity than the substrate.

[0010] An oxide layer is formed above each of the source/drain regions. A gate insulator is formed over the body region and oxide layer. The gate insulator is capable of storing a plurality of charges. A control gate is formed on the gate insulator.

[0011] Further embodiments of the invention include methods and apparatus of varying scope.

## **BRIEF DESCRIPTION OF THE DRAWINGS**

- [0012] Figure 1 shows a cross-sectional view of a typical prior art SOI semiconductor.
- [0013] Figure 2 shows a cross-sectional view of one embodiment for a planar NOR NROM cell using ultra-thin SOI.
- [0014] Figure 3 shows a cross-sectional view of one embodiment of two vertical NOR NROM cells of the present invention using ultra-thin SOI.
- [0015] Figure 4 shows a cross-sectional view of another embodiment of two vertical NOR NROM cells of the present invention using ultra-thin SOI.
- [0016] Figure 5 shows an electrical equivalent circuit of a NOR NROM flash memory array of the present invention.
- [0017] Figure 6 shows a cross-sectional view of yet another alternate embodiment of a vertical NOR NROM memory array of the present invention using ultra-thin SOI.
- [0018] Figure 7 shows an electrical equivalent circuit of a NOR NROM flash memory array of the present invention in accordance with the embodiment of Figure 6.
- [0019] Figure 8 shows a cross-sectional view of one embodiment of a planar NAND NROM cell of the present invention using ultra-thin SOI.
- [0020] Figure 9 shows a cross-sectional view of one embodiment of two vertical NAND NROM cells of the present invention using ultra-thin SOI.
- [0021] Figure 10 shows an electrical equivalent circuit of a NAND NROM flash memory array of the present invention in accordance with the embodiment of Figure 9.
- [0022] Figure 11 shows a block diagram of one embodiment of an electronic system of the present invention.

## **DETAILED DESCRIPTION**

[0023] In the following detailed description of the invention, reference is made to the accompanying drawings that form a part hereof and in which is shown, by way of illustration, specific embodiments in which the invention may be practiced. In the

drawings, like numerals describe substantially similar components throughout the several views. These embodiments are described in sufficient detail to enable those skilled in the art to practice the invention. Other embodiments may be utilized and structural, logical, and electrical changes may be made without departing from the scope of the present invention. The following detailed description is, therefore, not to be taken in a limiting sense, and the scope of the present invention is defined only by the appended claims and equivalents thereof.

**[0024]** Figure 2 illustrates a cross-sectional view of one embodiment of a planar NROM cell using ultra-thin silicon-on-insulator (SOI) technology. The NROM flash memory cell of Figure 2 is a NOR array cell with virtual ground bit lines.

**[0025]** The NROM flash memory cell is comprised of the silicon layer 201 on the insulator 202. The silicon 201 in an ultra-thin SOI cell is less than 100 nm (1000 Å). This layer 201 is comprised of two source/drain areas 220 and 221 that act as bit lines 220 and 221. In one embodiment, these areas 220 and 221 are n-type material. Alternate embodiments use p-type material if the substrate is an n-type material.

**[0026]** The body region 200 between the bit lines 220 and 221 is normally fully depleted in ultra-thin SOI. The body region 200 is comprised of ionized acceptor impurities 203 and ionized donor impurities 205. Two oxide areas 210 and 211 are deposited on the silicon 201.

**[0027]** A gate insulator 207, in one embodiment, is a composite structure of oxide-nitride-oxide (ONO) formed between the control gate 230 and the silicon layer 201. The control gate 230, in one embodiment, is a polysilicon material and extends in the 'x' direction in the NOR flash cell embodiment. The nitride layer 225 has two charge storage areas 231 and 232.

**[0028]** Alternate embodiments of the present invention use other gate insulators besides the ONO composite structure shown. These structures may include oxide-nitride-aluminum oxide composite layers, oxide-aluminum oxide-oxide composite layers, oxide, silicon oxycarbide-oxide composite layers as well as other composite layers.

[0029] In still other alternate embodiments, the gate insulator may include thicker than normal silicon oxides formed by wet oxidation and not annealed, silicon rich oxides with inclusions of nanoparticles of silicon, silicon oxynitride layer that are not composite layers, silicon rich aluminum oxide insulators that are not composite layers, silicon oxycarbide insulators that are not composite layers, silicon oxide insulators with inclusions of nanoparticles of silicon carbide, in addition to other non-stoichiometric single layers of gate insulators of two or more commonly used insulator materials such as Si, N, Al, Ti, Ta, Hf, Zr, and La.

[0030] Figure 3 illustrates a cross-sectional view of one embodiment of two vertical NOR NROM cells 350 and 351 of the present invention using ultra-thin SOI. The vertical embodiment provides for higher density memory arrays.

[0031] The cells 350 and 351 of Figure 3 each have source/drain areas 330 and 331 that operate as bit lines and are comprised of n+ doped silicon. Alternate embodiments use p-type material if the substrate is comprised of n-type material. Additional source/drain areas 320 and 321 for each transistor are formed at the top of a vertical oxide pillar 310. The left transistor 350 uses source/drain areas 320 and 331 while the right transistor uses source/drain areas 321 and 330. The upper source/drain areas 320 and 321 are separated by a grain boundary but are electrically coupled. The vertical oxide pillar 310 is an insulator between the two transistors 350 and 351.

[0032] Vertical epitaxial regrowth of amorphous layers is used to provide crystalline layers of ultra-thin silicon 300 and 301 along the sidewalls of the vertical oxide pillar 310. These layers are the ultra-thin silicon (i.e., < 100 nm) body regions 300 and 301 and are normally fully depleted. The direction of thickness of the silicon body region 300 and 301 is illustrated in each region. The left ultra-thin silicon body region is part of the left transistor 350 while the right body region 300 is part of the right transistor 351.

[0033] The gate insulator layer 307, in one embodiment, is a composite ONO structure. Alternate embodiments of this layer 307 are disclosed above. The control gate 330 is formed above this insulator layer 307 and is common to both transistors 350 and 351 such

that it acts as a word line in a memory array. In one embodiment, the control gate 330 is a polysilicon material.

**[0034]** Figure 4 illustrates a cross-sectional view of another embodiment of two vertical NOR NROM cells of the present invention using ultra-thin SOI. This embodiment has an architecture that is substantially similar to the embodiment of Figure 3 in that the ultra-thin silicon body regions 400 and 401 are formed by epitaxial regrowth along the sidewalls of the oxide pillar 410. The top source/drain areas 420 and 421 are formed at the top of the oxide pillar 410 and the common poly control gate 405 is formed over the gate insulator 420 coupling both transistors 450 and 451 by a word line.

**[0035]** However, in the embodiment of Figure 4, the bottom oxide layer 402 and 404 of the gate insulator 420 is thicker in the trench than in the previous embodiment. Additionally, the two source/drain areas of Figure 3 are replaced by a single n+ source/drain region 430 that is isolated between the portions of the thicker oxide layer.

**[0036]** Figure 5 illustrates an electrical equivalent circuit of a NOR NROM flash memory array of the present invention. This circuit can represent the planar embodiments of the present invention as well as the vertical embodiment of Figure 3.

**[0037]** The control gate 501 crosses all of the devices 510 – 512 in the array. The n+ source/drain regions 503 and 504 are used as virtual ground data or bit lines. As is well known in the art, the bit lines of the array are coupled to a sense amplifier in order to read data from the cells 510 – 512. The control gate 501 is the word line used to select the cells 510 – 512.

**[0038]** Figure 6 illustrates a cross-sectional view of yet another alternate embodiment of a vertical NOR NROM memory array of the present invention using ultra-thin SOI. This figure illustrates four vertical transistors 650 – 653. For purposes of clarity, only the transistors formed around the first oxide pillar 632 are described. The remaining transistors are substantially identical in structure and operation.

**[0039]** As in previous embodiments, the two ultra-thin silicon body regions 608 and 609 are formed by epitaxial regrowth along the sidewalls of the oxide pillar 632. The gate

insulator layers 601 and 602 are formed alongside of the silicon body regions 608 and 609. The n+ polysilicon gate structures 630 and 631 for each transistor 650 and 651 are then formed on the insulator layers 601 and 602.

[0040] The nitride layers 603 and 604 provide two charge storage areas 610 and 611 for each transistor 650 - 653. In the trench area, the lower oxide layer 605 has a thicker composition than the rest of the gate insulator layer. The above cells 650 - 653 are formed on a lower n+ region 620 on the substrate that acts as a common source/drain area, depending on the direction that each transistor is biased.

[0041] The upper n+ regions 660 and 661 are the second common source/drain area for each transistor 650 and 651. The upper n+ region 660 and 661 of each transistor is coupled to other transistors in the array by a bonding wire 640 or other conductive device.

[0042] Figure 7 illustrates an electrical equivalent circuit of a NOR NROM flash memory array of the present invention in accordance with the embodiment of Figure 6. This figure illustrates the respective cells 650 - 653 as described in Figure 6 above.

[0043] The control gates 701 - 704 are coupled to other cells in the array and act as word lines. Two of these control gates 701 - 704 are illustrated in Figure 6 as 630 and 631. The top common source/drain areas 660 and 661 are shown as virtual ground or data bit line 709 while the common source/drain area 620 is shown as virtual ground or data bit line 708.

[0044] Figure 8 illustrates a cross-sectional view of one embodiment of a planar NAND NROM cell of the present invention using ultra-thin SOI. This embodiment is comprised of the two source/drain regions 803 and 804 with the fully depleted body region 801 in the ultra-thin SOI. The two oxide regions 807 and 808 are formed above the n+ areas and the gate insulator 805 is formed over this architecture. In one embodiment, the gate insulator 805 is a composite ONO layer but can be any other type of material including those described above.

**[0045]** The control gate 806 is formed above the gate insulator 805. In the NAND embodiment, the gate 806 extends in the 'z' direction instead of the 'x' direction as in the NOR embodiment.

**[0046]** Figure 9 illustrates a cross-sectional view of one embodiment of two vertical NAND NROM cells 910 and 911 of the present invention using ultra-thin SOI. Each transistor 910 and 911 is comprised of a source/drain region 905 and 906 formed in a p-type substrate material. Second source/drain regions 920 and 921 are formed on top of the oxide pillar 930 and separated by the grain boundary while still electrically coupled. The source/drain regions 905, 906, 920, and 921 function as electrical connections down the row.

**[0047]** Epitaxial regrowth is used to grow ultra-thin silicon body regions 901 and 902 on the sidewalls of the oxide pillar 930. As in previous embodiments, these regions 901 and 902 are each less than 100 nm thick.

**[0048]** The gate insulator 950 is formed on top of the transistors 910 and 911. In one embodiment, the gate insulator 950 is an ONO composite layer. Alternate embodiments for the composition of this layer have been illustrated previously.

**[0049]** Control gates 907 and 908 for each transistor 910 and 911 respectively are formed from a polysilicon material on each side of the gate insulator 950. The control gates 907 and 908 are coupled to other transistors to act as word lines.

**[0050]** Figure 10 illustrates an electrical equivalent circuit of a NAND NROM flash memory array of the present invention in accordance with the embodiment of Figure 9. The two transistors 910 and 911 of Figure 9 are shown.

**[0051]** The n+ source/drain connection 1005 of Figure 10 corresponds to the two source/drain regions 920 and 921 of Figure 9. The word lines 1001 and 1002 of Figure 10 correspond to the control gate 907 and 908 respectively of Figure 9. The source/drain regions 905 and 906 formed in the substrate of Figure 9 correspond to the source/drain connections 1009 and 1007 of Figure 10.



[0052] The above embodiments are illustrated as n-channel type transistors. However, one of ordinary skill in the art will understand that the conductivity types can be reversed by altering the doping types such that the present invention is equally applicable to include structures NROM structures having ultra-thin silicon, p-channel type transistors.

[0053] The masking and etching steps used to form the ultra-thin silicon NROM flash memory cells of the present invention are not discussed in detail. The various steps required to form the above-described architectures are well known by those skilled in the art.

[0054] Figure 11 illustrates a functional block diagram of a memory device 1100 that can incorporate the ultra-thin SOI flash memory cells of the present invention. The memory device 1100 is coupled to a processor 1110. The processor 1110 may be a microprocessor or some other type of controlling circuitry. The memory device 1100 and the processor 1110 form part of an electronic system 1120. The memory device 1100 has been simplified to focus on features of the memory that are helpful in understanding the present invention.

[0055] The memory device includes an array of flash memory cells 1130. In one embodiment, the memory cells are NROM flash memory cells and the memory array 1130 is arranged in banks of rows and columns. The control gates of each row of memory cells is coupled with a wordline while the drain and source connections of the memory cells are coupled to bitlines. As is well known in the art, the connection of the cells to the bitlines depends on whether the array is a NAND architecture or a NOR architecture.

[0056] An address buffer circuit 1140 is provided to latch address signals provided on address input connections A0-Ax 1142. Address signals are received and decoded by a row decoder 1144 and a column decoder 1146 to access the memory array 1130. It will be appreciated by those skilled in the art, with the benefit of the present description, that the number of address input connections depends on the density and architecture of the memory array 1130. That is, the number of addresses increases with both increased memory cell counts and increased bank and block counts.

[0057] The memory device 1100 reads data in the memory array 1130 by sensing voltage or current changes in the memory array columns using sense/buffer circuitry 1150. The sense/buffer circuitry, in one embodiment, is coupled to read and latch a row of data from the memory array 1130. Data input and output buffer circuitry 1160 is included for bi-directional data communication over a plurality of data connections 1162 with the controller 1110). Write circuitry 1155 is provided to write data to the memory array.

[0058] Control circuitry 1170 decodes signals provided on control connections 1172 from the processor 1110. These signals are used to control the operations on the memory array 1130, including data read, data write, and erase operations. The control circuitry 1170 may be a state machine, a sequencer, or some other type of controller.

[0059] Since the NROM memory cells of the present invention use a CMOS compatible process, the memory device 1100 of Figure 11 may be an embedded device with a CMOS processor.

[0060] The flash memory device illustrated in Figure 11 has been simplified to facilitate a basic understanding of the features of the memory. A more detailed understanding of internal circuitry and functions of flash memories are known to those skilled in the art.

## CONCLUSION

[0061] In summary, the NROM flash memory cells of the present invention utilize ultra-thin SOI to provide a fully depleted body region. This eliminates the undesirable floating body effects experienced by partially depleted CMOS devices.

[0062] Although specific embodiments have been illustrated and described herein, it will be appreciated by those of ordinary skill in the art that any arrangement that is calculated to achieve the same purpose may be substituted for the specific embodiments shown. Many adaptations of the invention will be apparent to those of ordinary skill in the art. Accordingly, this application is intended to cover any adaptations or variations of the invention. It is manifestly intended that this invention be limited only by the following claims and equivalents thereof.